

27.10.2014

Fennostrength™ MLX

Polyamide/polyamine epichlorohydrine resin

Used for wet strength treatment of papers, preferably in a pH range of 6 – 10, e.g. laminate base paper, special- and tissue papers. Increases the retention of fillers and color pigments. Fennostrength MLX is a new development which combines very low level of total AOX, high active matter and very high efficiency.

Product Properties

Solid Content	approx. 21,8 %
Viscosity (20°C)	< 100 mPa.s
pH	approx. 2,5
Ionicity	cationic
Density (20°C)	approx. 1100 kg/m ³
Appearance	amber liquid

Product Safety

Please refer to the material safety data sheet for more instructions.

Delivery

Fennostrength MLX is delivered in 1000 kg containers.

Storage

2 months at temperatures < 25°C. At temperatures of < 0°C frozen resin should be thawed, mixed carefully and directly used.

Kemira makes this information available as an accommodation to its customers and it is intended to be solely a guide in customer's evaluation of the products. You must test our products, to determine if they are suitable for your intended uses and applications, as well as from the health, safety and environmental standpoint. You must also instruct your employees, agents, contractors, customers or any third party which may be exposed to the products about all applicable precautions. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. You assume full liability and responsibility for compliance with all information and precautions, and with all laws, statutes, ordinances and regulations of any governmental authority applicable to the processing, transportation, delivery, unloading, discharge, storage, handling, sale and use of each product. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use.

Fennosize are trademarks or registered trademarks of Kemira Oyj or its subsidiaries.

Kemira Oyj

P.O.Box 330 (Porkkalankatu 3)
FI-00101 Helsinki
Finland
www.kemira.com

Europe, Middle-East and Africa
Tel +358 10 8611
North America
Tel +1 770 436 1542

South America
Tel +55 11 2189 4900
Asia-Pacific
Tel +86 21 6037 5999